

# Technical Data

## ANTIFOULING SEAMATE SB 33



### Product description

Seamate SB 33 is a high build self-polishing antifouling based on specially formulated organotin polymer as binder. This binder dissolves slowly in seawater so that fresh antifouling is continuously exposed.

### Recommended use

As an antifouling for side and flatbottom areas on vessels operating at medium speed with drydocking intervals up to 60 months.

### Film thickness and spreading rate

|  | Minimum | Maximum |
|--|---------|---------|
| Film thickness, dry ( $\mu\text{m}$ )                | 75      | 150     |
| Film thickness, wet ( $\mu\text{m}$ )                | 145     | 290     |
| Theoretical spreading rate ( $\text{m}^2/\text{l}$ ) | 6.9     | 3.5     |

### Physical properties

|                 |                          |
|-----------------|--------------------------|
| Colour          | Light Red and Dark Red.  |
| Solids (vol %)* | 52 $\pm$ 2               |
| Flash point     | 26°C $\pm$ 2 (Setaflash) |

\*Measured according to ISO 3233:1998 (E)

### Surface preparation

#### Coated surfaces

Prior to paint application, all surfaces should be clean, dry and free from contamination. Remove surface contamination by high pressure fresh water cleaning. To be applied on a clean, dry approved primer/undercoat or intact self-polishing antifouling. Remove surface contamination by high pressure fresh water cleaning.

#### Other surfaces

The coating may be used on other substrates. Please contact your local Jotun office for more information.

### Condition during application

The temperature of the substrate should be minimum 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure correct drying.

### Application methods

|               |   |
|---------------|---|
| <b>Spray</b>  | Use airless spray   |
| <b>Brush</b>  | May be used but care must be taken to achieve the specified dry film thickness.   |
| <b>Roller</b> | May be used however when using roller application care must be taken to apply sufficient material in order to achieve the specified dry film thickness. |



## Application data

|                                   |  |
|-----------------------------------|--|
| <b>Thinner/Cleaner</b>            | Jotun Thinner No. 7                          |
| <b>Guiding data airless spray</b> |  |
| <b>Pressure at nozzle</b>         | 15 MPa (150 kp/cm <sup>2</sup> , 2100 psi.). |
| <b>Nozzle tip</b>                 | 0.53 - 0.78 mm (0.021 - 0.031").             |
| <b>Spray angle</b>                | 65 - 80°                                     |
| <b>Filter</b>                     | Check to ensure that filters are clean.      |

## Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- \* Good ventilation (Outdoor exposure or free circulation of air)
- \* Typical film thickness
- \* One coat on top of inert substrate

| <b>Substrate temperature</b>               | <b>5°C</b> | <b>10°C</b> | <b>23°C</b> | <b>40°C</b> |
|--|------------|-------------|-------------|-------------|
| <b>Surface dry</b>                         | 1 h        | 1 h         | 0.5 h       | 0.5 h       |
| <b>Through dry</b>                         | 1.5 h      | 1.5 h       | 1.5 h       | 1 h         |
| <b>Dry for launching</b> <sup>1</sup>      | 12-24 h    | 10-22 h     | 8-20 h      | 6-18 h      |
| <b>Dry to recoat, minimum</b> <sup>2</sup> | 10 h       | 9 h         | 6 h         | 4 h         |

1. The interval indicates the time which normally occurs in a drydocking situation where the drying time depends on the total film thickness of primer/antifouling applied. The drying time will increase with increasing film thickness.
2. The surface should be dry and free from any contamination prior to application of the subsequent coat.

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

## Recommended type of primer:

Jotamastic 87 with tie coat, Vinyguard Black/Brown, Vinyguard Silvergrey 88, Safeguard, Safeguard Universal.

## Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

## Handling

Handle with care. Stir well before use.

## Packing size

20 L.

Packing may vary from country to country according to local requirements.

## Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

**For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.**

## DISCLAIMER

*The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.*

### Head Office & Nordic

Jotun Paints  
P.O. Box 2021  
N-3248 Sandefjord  
Norway  
Phone +47 33 45 70 00  
Fax +47 33 46 46 13

### Europe

Jotun Paints (Europe) Ltd.  
Stather Road, Flixborough  
North Lincolnshire DN15 8RR  
United Kingdom  
Phone +44 172 44 00 000  
Fax +44 172 44 00 100

### Middle East

Jotun U.A.E Ltd. LLC.  
Al Quoz Industrial Area  
P.O Box 3671  
Dubai U.A.E  
Phone +971 4 3 39 50 00  
Fax +971 4 3 38 06 66

### South East Asia

Jotun (Singapore) Pte. Ltd.  
No 11-15, Sixth Lok Yang  
Road  
Jurong  
Singapore 628 111  
Phone +65 6265 4711  
Fax +65 6265 7484

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at [www.jotun.com](http://www.jotun.com)

ISSUED 12 FEBRUARY 2002 BY JOTUN PAINTS  
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED