

Technical Data

JOTAFLOOR SCREED



Product description

Jotafloor Screed is a high performance, trowel applied, three component, solvent free epoxy floor coating offering exceptional strength characteristics, resistance to a range of chemicals, and superior abrasion/wear properties. Generally applied at 5 mm thickness and above. (Seek advice from Jotun Technical Dept.)

Recommended use

The high strength impervious finish makes Jotafloor Screed ideal for heavy industrial areas such as:

- Steelworks
- Engineering plants
- Chemical production areas
- Oil refineries
- Dairies

Also ideally suited where heavy traffic is expected or a durable non-slip finish is required. Jotafloor Screed may be overcoated with Jotafloor Topcoat or Jotafloor Coating if different colours are required. Jotafloor Screed exhibits very high bond strength and adhesion characteristics making it an ideal repair material for concrete and floor joint edges.

Film thickness and spreading rate

	Minimum	Maximum	Typical
Film thickness, dry (μm)	4000	6000	5000
Film thickness, wet (μm)	4000	6000	5000
Theoretical spreading rate (m^2/l)	0.25	0.17	0.2

Comments

Jotafloor Screed can be applied at higher thicknesses to suit specific requirements. Request further information from Jotun Technical Department.

Physical properties

Colour	Colour of the graded aggregate
Solids (vol %)*	98 \pm
Flash point	>100°C (Setaflash)
Water resistance	Excellent
Abrasion resistance	Excellent
Solvent resistance	Excellent
Chemical resistance	Excellent Check chemical resistance values on Jotafloor chemical resistance chart.

*Measured according to ISO 3233:1998 (E)

Surface preparation

All concrete damaged by exposure to chemicals, contaminated by any substance or unsound in any way, shall be removed to expose sound concrete.

Other surfaces

Concrete surface preparation by using dust free captive blasting units, grinding equipment, sand blasting or high pressure water jetting is critical to achieving the right surface profile prior to paint application. Contact your local Jotun office for more information.

The coating may be used on other substrates. Please contact your local Jotun office for more information.

Condition during application

The temperature of the substrate should be minimum 12°C (preferably 15°C) and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. The moisture in the concrete should not exceed 4 % (by weight). The coating should not be exposed to oil, chemicals or mechanical stress until fully cured.

Application methods

Other

Nylon or steel trowel.

Mixing ratio (volume)

1.7 ltr Comp. A (base) to be mixed thoroughly with 1 ltr Comp. B (curing agent) before adding 24 kg graded aggregates. NO PART MIXING

Mixing

Mix the resin and curing agent well before adding the aggregate. A forced action drill and appropriate mixing paddle should be used. The three components are supplied in a 20 ltr. can that can be used as the mixing vessel.

Pot life (23°C)

25 min. (Comp. A + Comp. B only), 40 min. (mix. with aggregate).

Cleaner

Jotun Thinner No. 17 or fresh water.

Note

It is essential to apply Jotafloor Screed onto Jotafloor Screed Primer whilst the primer is still "tacky". See separate Technical Data Sheet.

This product should be applied by a trained specialist. Jotun can offer a list of Licensed Applicators on request to your local Jotun office.

Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- * Good ventilation (Outdoor exposure or free circulation of air)
- * Typical film thickness
- * One coat on top of inert substrate

Substrate temperature	15°C	23°C	40°C
Surface dry	10 h	6 h	3 h
Through dry	16 h	10 h	4 h
Cured	8 d	7 d	4 d
Dry to recoat, minimum	16 h	10 h	4 h
Dry to recoat, maximum ¹	96 h	96 h	48 h

² The surface should be free from chalking and contamination prior to application. If the maximum dry to recoat time is exceeded, please contact Jotun Paints for advice.

The given data must be considered as guidelines only. The actual drying time/times before

recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

Typical paint system

Jotafloor Screed Primer	1 x 150 µm	(Dry Film Thickness)
Jotafloor Screed and eventually	1 x 5000 µm	(Dry Film Thickness)
Jotafloor Topcoat	1-2 x 50 µm	(Dry Film Thickness)

Other systems may be specified, depending on area of use

Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

Handling

Handle with care. Stir well before use.

Packing size

1.7 L. Comp. A (base) and 1 L. Comp. B (curing agent). 24 kg graded aggregate.
Packing may vary from country to country according to local requirements.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

DISCLAIMER

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.

Head Office & Nordic

Jotun Paints
P. O. Box 2021
N-3248 Sandefjord
Norway
Phone +47 33 45 70 00
Fax +47 33 46 46 13

Europe

Jotun Paints (Europe) Ltd.
Stather Road, Flixborough
North Lincolnshire DN15 8RR
United Kingdom
Phone +44 172 44 00 000
Fax +44 172 44 00 100

Middle East

Jotun U.A.E Ltd. LLC.
Al Quoz Industrial Area
P.O Box 3671
Dubai U.A.E
Phone +971 4 3 39 50 00
Fax +971 4 3 38 06 66

South East Asia

Jotun (Singapore) Pte. Ltd.
No 11-15, Sixth Lok Yang
Road
Jurong
Singapore 628 111
Phone +65 6265 4711
Fax +65 6265 7484

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at www.jotun.com

ISSUED 13 FEBRUARY 2002 BY JOTUN PAINTS
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED