



Technical Data Sheet

INDUCRET®-KIS-2/5

Channel / ducting mortar

Art.-No. 5 50020

Properties:

INDUCRET-KIS-2/5 is a channel/ducting mortar with the following properties:

- cementitious
- highly resistant to sulphate attack
- easy to use at low temperatures
- can be used on horizontal, vertical and "overhead" areas.

INDUCRET-KIS-2/5 guarantees a strong bond to the concrete substrate.

Areas of application:

INDUCRET-KIS-2/5 is used as a PCC (Polymer modified concrete) concrete replacement system for the renovation and coating of concrete surfaces that are especially subjected to chemical contact:

- sewerage pipe systems
- rain overflow basins
- sewerage works
- sewerage collection
- retention ponds.

INDUCRET-KIS-2/5 is to be applied at a minimum thickness of 2mm up to maximum of 5mm.

Technical Data:

Particle size:	0.1 – 0.5 mm
Wet mortar density*):	2.12 kg/dm ³
Consumption:	2.00 kg/dm ³
Pot life*):	approx. 45 minutes
Expansion*):	+0.4% volume after 24 hours
(DIN 1164)*):	Compressive strength approx. 12 N/mm ² after 24 hours approx. 45 N/mm ² after 7 days approx. 61 N/mm ² after 28 days

Flexural strength*):	approx. 3.0 N/mm ² after 24 hours approx. 8.0 N/mm ² after 7 days approx. 9.0 N/mm ² after 28 days
----------------------	--

*) These values are valid for +20 °C and 65% relative humidity.

Cleaning:

Thoroughly clean tools after use with water.

Packaging:

25 kg bags.

Storage:

Cool and dry, 9 months in the original unopened packaging above +10 °C. Use opened packaging promptly.

Surface preparation:

Before application of INDUCRET-KIS-2/5 the substrate is to be intensively pre-wetted but during application of INDUCRET-KIS-2/5 the relevant substrate may however only be matt damp. Surface preparation is necessary such as e.g. grit or shot blasting, high-pressure water jetting if no previous restoration work was carried out. Cementitious surfaces must be solid with a good grip and be load-bearing, free from cement laitance, loose particles as well as adhesion inhibiting substances (oil, grease, rubber marks, paint residues or other contamination).

Average surface tensile strength: min. 1.5 N/mm²

Product preparation:

1. Production of the repair mortar:
 - INDUCRET-KIS-2/5 = 25.0 kg
 - Water = approx. 5.0 – 5.25 litres

INDUCRET®-KIS-2/5

Fill a mixing vessel with up to 80% of the above mentioned water quantity.

Add the required quantity of INDUCRET-KIS-2/5 under constant mixing with a suitable stirrer (approx. 300 rpm). Mix thoroughly for approx. 3 - 5 minutes to a lump free mortar. Add the remaining 20% water and mix for a further 2 minutes. Use a forced paddle mixer for preparing large quantities. Only mix as much material as can be used within the stated working life.

Application tools:

Hand trowel, steel lath, hand smoother, rubbing sponge.

Application by hand:

Apply INDUCRET-KIS-2/5 on prepared substrate to the desired thickness. Pre-fill pores and cavities by troweling or brusting.

After the required waiting time smooth the surface. Do not rework surface with a wetted brush or trowel. For a smooth transition in the repaired surface it is possible to rub with a dry sponge.

Wet application with spray equipment:

When spraying in wet form, a bonding slurry is not required. The substrate must have a matt damp surface after thorough saturation with water. After mixing, the material is applied to the substrate with appropriate spray equipment using a MAWO-nozzle. To ensure even coverage, an industrial compressor is required (min. 5m³ air/5 bar pressure).

Pump system PFT:

PFT MULTIMIX batch mixer combined with
PFT N 2 FC 400

Conveying pump/ Rotor stator D8-1.5
25mm diameter mortar hose

Spray gun with 35/10mm nozzle (MAWO)

Pump system Inotec:

inoMIX ZM 80 turbocharged compulsory mixer
combined with

inoBEAM F21 light feeding pump/Rotor stator D8-1.5
25mm diameter mortar hose

Spray gun with 35/10mm nozzle (MAWO)

Material application:

Through introduction of compressed air at the spray nozzle, the material should exit the nozzle in a uniform circular pattern. During the first spray coat application, blow holes, honeycombs, voids behind the rebar, irregularities in the wall, etc, should be filled and evened out. The second spray coat should be used to build up desired material thickness, which can then be finished with proper smoothing methods.

Curing and protection:

Protect the surface for at least one day after application of INDUCRET-KIS-2/5 using suitable measures (e.g. covering with polythene) against rapid drying out resulting from direct sunlight, draughts and/or high temperature fluctuations. After waiting for at least one day further suitable surface protection systems can be applied/carried out.

Health and safety:

INDUCRET-KIS-2/5 contains cement that forms an alkaline reaction with moisture. Therefore contact with the eyes and skin is to be avoided and mortar splashes are to be immediately and thoroughly washed off with plenty of water. Seek medical attention from an eye specialist when contact with eyes occurs. Store INDUCRET-KIS-2/5 out of the reach of children.

Important advice:

- The application temperature range lies between +5 °C and +35 °C. Lower temperatures and cold gauging water delay the strength development. Higher temperatures accelerate the strength development.
- Protect areas not be treated from the effects of INDUCRET-KIS-2/5.

INDUCRET®-KIS-2/5

- Applications that are not clearly explained in this technical data sheet may only be carried out after consultation with and written confirmation from the Technical Services Department of SCHOMBURG ICS GmbH.
- When the mortar INDUCRET-KIS-2/5 is to be spray applied then separate technical advice is to be requested.

Please observe a current EU health and safety data sheet.

GISCODE: ZP1